

# EIKKENS Cetol Clearcoat HB plus

1/3 pages November 2017

**Description** 

Colourless, satin gloss, high build, preservative for protected east or south facing exterior timber. Contains binary light stabilizers (improved UV resistance), based on alkyd resin.

**General Notes** 

Main characteristics Colourless with improved UV resistance.

The wood grain remains visible.

Microporous, resulting in a humidity-controlling system.

Water repellent.

Contains mould and algae inhibitors.

Use: Used as a topcoat over Cetol HLSe or Cetol Clearcoat LB plus on

protected, south or east facing timber structures.

As a maintenance system on intact – still sufficiently pigmented –

Cetol HLSe, Cetol Novatech or Cetol Filter 7 plus coats.

**Application Data** 

Conditions of application: Application temperature: 5-30°C.

Maximum relative humidity 85%

Method: For best results use a longhaired pure bristle brush.

Stir thoroughly before use.

Thinning: Apply the product unthinned.

Cleaning of equipment: Clean immediately after use with Mineral Turps/white spirits.

Recommended film thickness: Dry: 40 microns per coat.

> Wet: 90 microns per coat.

Coverage rate: Dressed Timber: 12m<sup>2</sup> per litre.

> 6-10m<sup>2</sup> per litre. Band Sawn Timber: Smooth Plywood: 12m<sup>2</sup> per litre. Band Sawn Plywood: 6-10m<sup>2</sup> per litre.

The coverage rate greatly depends on the method of application being

used and the nature of the substrate to be coated.

Drying times at 20°C/ Dust dry after approximately 3-5 hours.

65% relative humidity: Recoatable after approximately 16 hours with further coats of Cetol

Clearcoat HB plus.

All coatings must be thoroughly dry before applying a further

coat.

Low temperatures and/or high humidity can delay drying times. At temperatures below 10°C the drying process will be delayed. Drying time may also be delayed when used internally with

insufficient air flow/ventilation.

100.65

2/3 pages November 2017

## **Practical Application Data**

#### Preparation

Timber surfaces must be sanded (if appropriate), clean and dry, with dust, dirt, wax and grease removed. Mould and algal growth must be eradicated using a suitable fungicide. The moisture content of timber must not exceed 18%. Degrease timber surface by wiping with white spirits. Preservative pre-treatments must be fully dry before coating.

#### **Application**

For protected, south or east facing doors and timber surfaces apply either

1 coat of Cetol HLSe & 2 coats Cetol Clearcoat HB plus.

Or

1 coat of Cetol Clearcoat LB plus & 2 coats Cetol Clearcoat HB plus.

Product should be applied in a full flowing coat following the direction of the grain. The first coat should be applied to all surfaces of components prior to installation. Avoid overbrushing.

#### Maintenance

Remove surface dust and dirt by washing. Any loose material should be removed using a stiff (non-metallic) bristle brush. If water and/or detergent is necessary to remove any stubborn dirt, ensure that the timber is thoroughly rinsed and completely dry. Mould and algal growth must be eradicated using a suitable fungicide.

If excessive weathering has occurred giving a grey appearance, the surface must be abraded back to clean bare timber before re-coating. Bare timbers should then be touched in with a coat of Cetol Clearcoat LB plus or Cetol HLSe before applying a maintenance coat of Cetol Clearcoat HB plus to the whole area.

## **Properties**

Density: 0.98 kg/dm<sup>3</sup>.

Solids content: 68% by weight = 62% by volume.

Gloss level: Satin gloss finish.

Durability: Good (1-2 years for a 3 coat system on protected east or south facing

timber). Not recommended for unprotected north or west facing

applications.

Durability depends to a large extent on the wood species involved, design, quality of construction and glazing, condition of indoor paintwork, method of application, elevation of the building concerned,

degree of pigment, film thickness, etc.

### **Further Information**

Container sizes: 1 litre, 2.5 litre cans.

**100.65** 3/3 pages November 2017

## **Health and Safety Aspects**

Flash point (DIN 53213): 62°C

Transport code: N/A

Hazchem code: N/A

Government regulations: The user of this product is required to comply with the national

statutory regulations for health and safety at work and waste disposal.

#### **Points to Note**

- Although Cetol Clearcoat contains UV blockers it will not provide the same UV protection as a pigmented Cetol HLSe or Filter 7 plus coating. Cetol Clearcoat should only be used on protected east or south facing timber.
- Test all products prior to use.
- The use of flat sawn timber (crown/arrowhead grain pattern) in high sunshine areas will significantly reduce the life span of your coating. Flat sawn timber (particularly cedar) has a much higher tendency to distort than quarter sawn timber. Sorting of quarter sawn timber for use in high sunshine areas prior to fixing or manufacture is recommended by BRANZ in their publication "BRANZ Selecting Timber Guide (August 2004)". Coating life span can be significantly reduced when used in elevated, seaside or exposed north facing situations.

# **Please Note**

• Every care is taken to ensure that the information provided in this data sheet is accurate. Jac Jay Limited is unable to guarantee results as it has no control over the conditions under which products are applied, the substrate or the application. The customer has to determine the suitability of the delivered products or information for its intended purpose.